



PRODUCT TYPE

Performance E-wood Second Grade

DIMENSIONS EN 315

Dimensions	Lenght	2500
	Width	1220
	Thickness	12
	Layer	7

WOOD SPECIES

Face	Ewood
Long grained	Poplar
Short grained veneers	Poplar

DENSITY EN 323

Density average	425-520	Kg/m ³
-----------------	---------	-------------------

BENDING STRENGTH EN 310

Modulus of Elasticity (Long Grained)	3230-4000	N/mm ²
Modulus of Elasticity (Short Grained)	4400-5500	N/mm ²

BONDING QUALITY EN 314

Class 1	OK
---------	----

MOISTURE CONTENT EN 322

% Moisture content	[6% -14%]
--------------------	------------

FORMALDHEYDE EMISSION EN12460-3

Classification E1	< 3.5 mg HCHO/(hm ²)
-------------------	----------------------------------

FIRE RESISTANCE EN 13501-1

Classification	D-s2, d0
----------------	----------