




Test Result for LHMA004

Sample Description	P21	Model No:	LHMA004
Date of Test	2017-11-10	Test Person	Jane
Test Temperature	25	Test Humidity	50
Width of Test Sample(mm)	39.45	Thickness of Test Sample(mm)	24.51
Joist Distance(mm)	400	Sectional Area(mm ²)	966.92
Breaking Load(N)	1436.0	Static Bending Strength(MPa)	36.36
Force Increment(N)	244.1	Bending Increment(mm)	1.51
Slope	162	Modulus of Elasticity(MPa)	4462



ZHEJIANG NEW INSIGHT MATERIAL TECHNOLOGY CO., LTD.
浙江新远见材料科技股份有限公司